

GP Max 5

Automotive Film Series

Performance Data:

Transmitted	5%	% Visible Light
Reflected	7%	
Glare Reduction	94%	
Transmitted	18%	% Total Solar Energy
Reflected	21%	
Absorbed	61%	
Shading Coefficient (SC)	0.41	
Solar Heat Gain Coefficient (SHGC)	0.36	
U Factor	0.95	
UV Rejection	≥ 99%	
Total Solar Energy Rejected (TSER)	64%	
IR Rejection*	81%	
Infrared Energy Rejection (IRER)	63%	

Read in accordance with National Fenestration Rating Council (NFRC) standards and calculated on single pane 6mm (1/4") clear glass.

*IR Rejection is tested in the IR range of 780 to 2500 nanometers.

Reported values are typical properties and should not be used as a specification. Since only the user is aware of the specific conditions in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for that intended use. If the specific conditions of use are critically dependent on any of the properties of the product, or if you need further information, contact Madico, Inc. or your local Madico film dealer.



mepfilms

GP Max 20

Automotive Film Series

Performance Data:

Transmitted	20%	% Visible Light
Reflected	6%	
Glare Reduction	78%	
Transmitted	40%	% Total Solar Energy
Reflected	8%	
Absorbed	52%	
Shading Coefficient (SC)	0.65	
Solar Heat Gain Coefficient (SHGC)	0.57	
U Factor	1.02	
UV Rejection	≥ 99%	
Total Solar Energy Rejected (TSER)	43%	
IR Rejection*	49%	
Infrared Energy Rejection (IRER)	35%	

Read in accordance with National Fenestration Rating Council (NFRC) standards and calculated on single pane 6mm (1/4") clear glass.

*IR Rejection is tested in the IR range of 780 to 2500 nanometers.

Reported values are typical properties and should not be used as a specification. Since only the user is aware of the specific conditions in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for that intended use. If the specific conditions of use are critically dependent on any of the properties of the product, or if you need further information, contact Madico, Inc. or your local Madico film dealer.



mepfilms

GP Max 35

Automotive Film Series

Performance Data:

Transmitted	35%	% Visible Light
Reflected	7%	
Glare Reduction	61%	
Transmitted	41%	% Total Solar Energy
Reflected	9%	
Absorbed	49%	
Shading Coefficient (SC)	0.65	
Solar Heat Gain Coefficient (SHGC)	0.57	
U Factor	1.01	
UV Rejection	≥ 99%	
Total Solar Energy Rejected (TSER)	43%	
IR Rejection*	58%	
Infrared Energy Rejection (IRER)	41%	

Read in accordance with National Fenestration Rating Council (NFRC) standards and calculated on single pane 6mm (1/4") clear glass.

*IR Rejection is tested in the IR range of 780 to 2500 nanometers.

Reported values are typical properties and should not be used as a specification. Since only the user is aware of the specific conditions in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for that intended use. If the specific conditions of use are critically dependent on any of the properties of the product, or if you need further information, contact Madico, Inc. or your local Madico film dealer.



mepfilms

GP Max 45

Automotive Film Series

Performance Data:

Transmitted	47%	% Visible Light
Reflected	8%	
Glare Reduction	48%	
Transmitted	51%	% Total Solar Energy
Reflected	9%	
Absorbed	40%	
Shading Coefficient (SC)	0.73	
Solar Heat Gain Coefficient (SHGC)	0.64	
U Factor	1.02	
UV Rejection	≥ 99%	
Total Solar Energy Rejected (TSER)	37%	
IR Rejection*	48%	
Infrared Energy Rejection (IRER)	35%	

Read in accordance with National Fenestration Rating Council (NFRC) standards and calculated on single pane 6mm (1/4") clear glass.

*IR Rejection is tested in the IR range of 780 to 2500 nanometers.

Reported values are typical properties and should not be used as a specification. Since only the user is aware of the specific conditions in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for that intended use. If the specific conditions of use are critically dependent on any of the properties of the product, or if you need further information, contact Madico, Inc. or your local Madico film dealer.

